

Mariblen Mask TP

The Mariblen Mask TP's main ingredient is collagen which is made of dermis of Tilapia. And it is the raw material for the exclusive use of molding machined cosmetics into the shape of a sponge sheet. The denaturing temperature is higher than other fish, and the collagen derived from tilapia dermis is stable. The Mariblen Mask TP which incorporates this has the touch peculiar to collagen with high moisture-holding ability. The products are provided in 3 kinds of forms such as A4, A5-size sheets, facial mask.

Marine Collagen Sheet



A5/A4 sheets

These are plain sheets provided in convenient A5 and A4 sizes. They can be cut into smaller shapes or used just as they are.

Full Face

The prefabricated masks are intended for use over the entire face. They have openings for facial features which make them easy to use.



Ingredients of Mariblen Mask TP



Name of ingredients	INCI Name
Collagen	COLLAGEN
Cellulose powder	CELLULOSE
Hydrogenated isoparaffin	HYDROGENATED POLYISOBUTENE
Polyoxypropylene stearyl ether	PPG-15 STEARYL ETHER
Polyoxyethylene (20E.O.)sorbitan tristearate	POLYSORBATE 65
Lavender Oil	LAVANDULA ANGUSTIFOLIA(LAVENDER) OIL

The content in this document is prepared based on documents and experimental data available at the time; however, the content does not comprise a guarantee. Please note in advance that the content described in this document may be changed depending on the circumstances. All intellectual property rights including copyrights and design rights of data described here and related documents belong to Koken Co., Ltd., and any unauthorized reproduction, reprinting or citation is strictly prohibited. Please refer to the MSDS of the product in advance for the safe use of these ingredients. In addition, care should be taken to comply with the laws and regulations related to the Pharmaceutical Affairs Law in each country on expressions concerning consumer products.

Mariblen Mask TP

Incredibly moisture absorbent

Incredible moisture retention




Moisture absorbent (what times of own weight)

● Mariblen Mask TP sheets absorbed approximately 40 times their own weight in moisture, which was approximately 7 times that absorbed by nonwoven fabric.

Moisture retention rate per unit weight after 30 minutes

● The sheets were left in an incubator at 37°C for 30 minutes, the percentage of water retention was measured after 30 minutes and the results were 85% for Mariblen Mask TP, and 70% for nonwoven fabric.



From in-house data

Observation by electron micrographs

● We have observed electron micrographs of Mariblen Mask TP. These showed that Mariblen Mask TP has holes of approximately 100 μm in diameter.

Product No.	Product Name	Specifications(Thickness 1mm)	Packing
MTP5025	Mariblen Mask TP A5 sheets	148×210	250 sheets/packet 250 sheets x 4 packets/box
MTP4005	Mariblen Mask TP A4 sheets	210×297	50 sheets/packet 50 sheets x 4 packets/box
MTP2005	Mariblen Mask TP Full Face	——	50 sheets/packet 50 sheets x 4 packets/box